



MONOBASE RU / MONOSIDERAL

THE ULTIMATE HARD-COAT, INTEGRALLY COLORED STUCCO DECORATIVE SYSTEM

1.0 DESCRIPTION

1.1 General

Monobase RU / Monosideral hard-coat stucco system is a cementitious exterior wall coating system yielding a durable, water-repellent colored finish. A blended composition of Portland cement, lime and non-synthetic chemical additives, **Monobase RU** and **Monosideral** perform like a protective skin that does not trap moisture, thus allowing substrates to breathe naturally and providing the unique balance of water repellency and exceptional vapor permeability. The combination of **Monobase RU** and **Monosideral** is the ultimate traditional approach in exterior decorative coating. The unique and revolutionary composition and reinforcing fibers of **Monobase RU** combined with the very specific integral color formulation of **Monosideral**, yield a durable, fade resistant, colored finish to be applied by hand troweling or machine spraying.

Monosideral is available in many attractive integral colors while custom colors are available upon request. The precise blend of calibrated sand, fibers and chemical additives, allows for vapor permeability and superb resistance to temperature variations.

2.0 MATERIALS

2.1 Coatings

Monobase RU (Basecoat)

Monobase RU consists of a factory-blended Portland cement, lime, sand, additives and proprietary admixture, available as a 66 lb. (30 kg) bag of factory blended mix requiring only the addition of potable water at the job site.

Monosideral (Finish Coat)

Monosideral consists of a factory-blended white Portland cement with pigments, additives (water repellent agents, UV resistant agents) and proprietary admixture. **Monosideral** is available as a 66 lb. (30 kg) bag of factory blended pre-sanded mix requiring only the addition of potable water at the job site.

2.2 Accessories

Metal Furring and Lath

The lath and accessories shall comply with ASTM C-847 and zinc coated (galvanized) steel meeting ASTM C-525 and shall be of 1.75, 2.5 or 3.4 weight per square yard as required by the applicable building code. Perform work in accordance with ASTM C-841, ASTM C-847, ASTM

C-1063 and ML/SFA specifications. Use fasteners recommended by fastener manufacturer for securing lath to wood, steel supports or bricks. Fasteners shall be spaced at a minimum of 6" and shall provide a minimum 1/8" (3.18 mm) clearance from the substrate after installation. The maximum overall wall coating thickness, using the minimum wire noted in this section, shall be 1/2" (12.7 mm). Companies specializing in performing the installation of Metal lath and trim accessories shall be approved and experienced, performing the installation according to the applicable building code.

Wire-Fabric Lath

Wire-fabric lath shall be a minimum Number 20 gauge; 1" (25.4 mm) galvanized steel. The furring and self-furring requirements shall be as described for metal lath in section 2.2. Wire-fabric lath shall be in compliance with ASTM 933-80 (welded) and ASTM 1032-86 (woven).

Weather-Resistive Membrane

A weather-resistive membrane is required over all substrates; exceptions being concrete, masonry surfaces and specific insulation board products. The weather-resistive membrane shall be minimum Grade D building paper complying with Federal Specification UUB-790A. The weather-resistive membrane shall be installed according to the applicable building code.

Plywood

The plywood substrates shall be in compliance with US DOC PS 1-95 and shall be minimum 7/16" (11.1 mm) in thickness.

Oriented Strand Board

Oriented Strand Boards shall be in compliance with US DOC PS-2-95, the American Plywood Association for Exposure 1 and shall have a minimum thickness of 7/16" (11.1 mm).

Gypsum Sheathing Board

The boards shall be water-resistant core gypsum sheathing in compliance with ASTM C 79-95.

Fiberboard

Asphalt-impregnated fiberboard shall be in compliance with ANSI/AHA A194.1-1985 as a regular density and shall have a minimum thickness of 1/2" (12.7 mm).

Caulk

The acrylic latex sealant shall be in compliance with ASTM C-834 and installed according to local building codes. Penetrations through the coating shall be caulked to prevent water penetration. Allow 48 hours minimum drying time prior to installing the sealant.

3.0 MIXING INSTRUCTIONS

3.1 Monobase RU

Mix approximately 1 1/2 gallons (6 quarts/ 6 liters) of clean, potable water to each bag of **Monobase RU**. Mix in a clean standard batch mixer for no less than 5 minutes to yield a good plasticity and homogeneous mix. Do not re-temper the material, add additional water or use partially set or frozen material in the mix. **Do not over-mix**. Repeat the mixing procedure and add the same amount of water with every batch.

3.2 Monosideral

Approximately 5 quarts (1 ¼ gallons) of clean potable water is to be added per bag of **Monosideral**. Mix in a clean standard stucco-mixing machine for a maximum of 10 minutes to yield good plasticity and a homogeneous mix. Do not over mix. For best results, pour 10 quarts (2.5 gallons) of potable water in the mixer, followed by 2 bags of **Monosideral**. Then add the remaining required water and 2 more bags. Allow to mix until a good homogeneous mix is achieved. Repeat the mixing procedure and add the same amount of water with every batch to avoid color variations. Do not re-temper the material in the mixer nor use partially set or frozen material in the mix. This may cause color variation.

4.0 INSTALLATION

4.1 First Step: Base Coat - Monobase RU

i. Application over Concrete and Masonry Surfaces

Surface Preparation

Surfaces must be free of all bond-inhibiting materials, including dirt, efflorescence, from form oils and other foreign particles. Paint, loose or damaged material must be removed by water blasting, sandblasting or mechanical wire brushing and repaired. Irregular surfaces must be resurfaced, patched or leveled to required tolerance and smoothness. Refer to ASTM C-926 for complete details on preparation and required condition of surfaces to receive Portland cement stuccos and recommended construction practices when installing stucco. Dampen excessively dry and overheated substrates before application.

Trowel Application

Apply **Monobase RU** directly over concrete, masonry or lath surface with a clean, stainless steel trowel in one or two coats for a thickness of 3/8" (9.53 mm) minimum according to substrate and surface conditions. Once applied, the working time for material is up to 20 minutes, according to ambient temperatures and surface condition. Application thickness varies depending on the pattern or texture desired.

Spray Application

Apply **Monobase RU** with a conventional plaster pump or a hand-held spray gun (refer to section 5.6) directly over the concrete, masonry or lath surface. Hold the spray nozzle at the same distance and move with a steady, even stroke building to the desired thickness. Apply an even coat to ensure full coverage in a one coat for a total thickness of 3/8" (9.53 mm) thickness, according to the substrate and surface conditions. Once applied the working time is up to 20 minutes according to ambient temperatures and surface condition.

Important: Apply **Monobase RU** in a continuous application, always working to a wet edge to eliminate cold joints. Arrange for the completion of an entire area. Avoid installation in direct sunlight. It is recommended that newly applied **Monobase RU** be fogged and kept damp for 48 hours.

ii. Application over Brick

Metal lath shall be installed as described in Section 2.2 of this document. Use corrosion-resistant fasteners for lath attachment and allow a minimum fastener penetration of 1" (25.4 mm) into the brick substrate. **Monobase RU** shall be applied with a stainless steel trowel or spray equipment directly over the lath to a minimum thickness of 3/8" (9.53 mm) which shall be

embedded in the coating and completely covered. Level the coating until a smooth plumb surface is achieved.

iii. Application over Solid Backing

A weather resistive membrane is installed as described in Section 2.2 of this document. The lath is installed as described in Section 2.4 of this document. Use corrosion-resistant fasteners for lath attachment and allow a minimum fastener penetration of 1" (25.4 mm) into wood framing. **Monobase RU** shall be applied with a stainless steel trowel or spray equipment directly over the lath to a minimum thickness of 3/8" (9.53 mm) which shall be embedded in the coating and completely covered. Level the coating until a smooth plumb surface is achieved.

iv. Plywood, Oriented Strand Board, Gypsum Sheathing, Fiberboard...

All shall be fastened directly over wood or steel framing in accordance to the applicable building code. The weather-resistive membrane, lath and coating shall be installed according to Section 2.2 of this document.

4.2 Second step: Finish Textured Coat – Monosideral Application

Trowel Application

Mist **Monobase RU** surface with water prior to **Monosideral** application. Apply **Monosideral** directly over **Monobase RU** surface with a clean, stainless steel trowel in one coat at a thickness of 3/16" (4 mm) minimum thickness to 1/4" (6 mm) maximum thickness according to substrate and surface conditions. Once applied the working time is up to 20 minutes according to ambient temperatures and surface condition. Trowel **Monosideral** to required tolerance. A fine sand finish texture may be achieved using a sponge, wood or plastic float.

Spray Application:

Mist **Monobase RU** surface with water prior to **Monosideral** application. Apply **Monosideral** with a conventional plaster pump (refer to section 5.6 for pump information) directly over the **Monobase RU** surface. Hold the spray nozzle at the same distance and move with a steady, even stroke building to the desired thickness. Apply an even coat to ensure full coverage in a one coat for a total thickness of 3/16" (4 mm) to 1/4" (6 mm) minimum thickness according to the substrate and surface conditions. Once applied the working time is up to 20 minutes according to ambient temperatures and surface condition. Trowel **Monosideral** to required tolerance and texture with a sponge, wood or plastic float.

Important: Apply **Monosideral** in a continuous application, always working to a wet edge to eliminate cold joints. Arrange for the completion of an entire area. Avoid installation in direct sunlight. It is recommended that newly applied **Monosideral** be fogged and kept damp for 48 hours.

Limitations

Apply **Monobase RU** and **Monosideral** when surface and ambient temperatures are above 45° F (8° C) and below 95° F (35° C) during application and drying period. Do not apply to overheated, excessively dry or frozen substrate, or during periods of high winds. **Monobase RU** and **Monosideral** should not be applied on horizontal, below grade or water immersed surfaces. **Monobase RU** is not recommended for applications to horizontal surfaces with the exception being that it can be applied on ceilings only over metal lath. Distance to grade varies with

climate and local building codes. Allow sufficient distance to prevent dirt, snow, ice and puddling water to be in contact with the coatings. Parapets should be protected with coping. Protect the coating from rain, freezing for at least 24 hours and from uneven and excessive evaporation during hot temperatures by moist curing. Due to the natural ingredients which make-up **Monobase RU** and **Monosideral** or the nature of the substrate, the development of efflorescences may naturally occur and appear on the surface of **Monobase RU** and **Monosideral**. Please refer to the maintenance specifications for clean-up.

5.0 MISCELLANEOUS

5.1 Packaging

Monobase RU: 66 lb. (30 kg) bag of powder (paper bag with moisture barrier)

Monosideral: 66 lb. (30 kg) bag of powder (paper bag with moisture barrier)

5.2 Coverage

Monobase RU: ~ 20 to 25 sq. ft. per bag of at 3/8"

Monosideral: ~ 30 to 35 sq. ft. per bag at 1/4" thickness

~ 45 to 50 sq. ft. per bag at 3/16" thickness

(Coverage is approximated and is given for estimating purposes only. Actual jobsite coverage may vary according to substrate conditions and application techniques.)

5.3 Storage and Shelf Life

Shelter in a dry environment and away from extreme heat, direct sunlight, rain and freezing. Shelf life is 6 months in the original sealed packaging, properly sheltered.

5.4 Control Joints

Install control joints as specified by the design professional, builder and conforming to conventional three-coat plaster details or the applicable building code. As a minimum, control joints are required in areas where structural movement occurs, at floor line in wood frame construction and at building expansion and openings

5.5 Professional Qualifications

Installation shall be performed by contractors with a minimum of 5 years documented experience in cement plastering or approved by Sider-Crete, Inc. All applicators should be able to provide several references from general contractors, architects or other applicable references for review by Sider-Crete, Inc.

5.6 Technical Application Assistance

Contact Sider-Crete, Inc. at **Toll Free: 888-743-3750** for all technical inquiries.

5.7 Hand-Held Spray Gun and Plaster Pumps

Approved hand-held spray guns and manufacturers

- Sablon spray gun (Ref # 32277 or # 32278) by Maco-Meudon
- Wall model 4 holes spray gun by ACPO
- Spotting model by ACPO
- Wall model 1 hole by ACPO

Recommended plaster pumps and manufacturers

- P11 Series, Tommy Gun A3 series, S5 Rotor/Strator Pumps & Mixers by Putzmeister
- And most mortars and plasters sprayers and mixers.

Contact Sider-Crete, Inc. for availability and additional information.

5.8 Clean Up

Monobase RU and **Monosideral** clean up with water prior to drying. Clean tools and equipment after use with water. Clean up and remove all debris and materials from the site caused by the installation according to federal, state and local regulations and dispose of waste in an approved landfill.

5.9 Commercial Names

MONOBASE RU

MONOSIDERAL

*And now, enjoy using **MONOBASE RU** and **MONOSIDERAL** and benefit from this superior traditional textured decorative wall coating developed by Sider-Crete, Inc., leaders of technological advancements for the construction industry.*

While every effort has been made to be comprehensive and accurate, the publisher cannot accept any liability for omissions or errors. Users should contact Sider-Crete for the product(s) referred to in this specification to ensure that any information used to make decisions about the product is as up-to-date and complete as possible.